

# SAITE TECHNOLOGY VIET NAM JSC

# VRLA AGM Battery

BT-12M12AC[12V12Ah]



### Seneral Features

- Designed floating charging service life: 8 years (25°C)
- Sealed and maintenance free operation
- Safety valve installation for explosion proof
- Low self-discharge characteristic
- Wide operating temperature range from 0°C~40°C
- Lead Aluminum calcium Tin alloy high energy, prevent corrosion


# **Application**

- DC power supply
- UPS/EPS power supply
- Electrical devices & instruments
- Security and fire alarm systems
- Telecom stations and power stations
- Medical equipment
- Emergency lighting systems

### **Physical Specifications**

Nominal Voltage	Nominal Capacity (20HR)		Dime	nsion		Internal	Standard	
		L	W	Н	TH	Weight ±3%	Resistance (In full charge status)	Terminals
12V	12AH	151±2mm	98±2mm	95±2mm	100±2mm	Approx3.75g (8.60lbs)	≤17.0mΩ	F01/F02 (standard)

# X Dimensions



# Constant-Voltage Charge

Rated Capacity	
20 hour rate (0.65A)	13.00AH
10 hour rate (1.20A)	12.00AH
5 hour rate (2.04A)	10.2AH
27 minute rate( 12.0A)	7.00AH
7 minute rate (36.0A)	4.90AH
( /	
Capacity affected by T	emperature
	emperature
Capacity affected by T	-
Capacity affected by T 40°C(104°F)	103%

#### **Cycle Application**

Cycle Application								
1. Limit initial current less than 3.0A.								
2. Charge until battery voltage (under charge) reaches 14.1V to 14.4V at 25°C(77°F).								
3. Hold at 14.1V to 14.4V until current drop to under 0.084A for at least 3 hours.								
4. Temperature compensation coefficient of charging voltage is -30mV/°C.								
Standby Service								
1. Hold battery across constant voltage source of 13.6to 13.8 volts with current limit3.0A continuously .When held at this voltage , the battery will seek its own current level and maintain itself in a fully charge status.								
2. Temperature compensation coefficient of charging voltage is -18mV/°C.								

A NOTE : The battery should be charged within 6 months of storage, Otherwise, permanent loss of capacity might occur as a result of sulfation








# **Battery Discharge Table**

End Voltage (V)	Minute (M)					Hour (H)							
	5	10	15	30	45	1	1.5	2	3	5	8	10	20
Constant Current Discharge Data Sheet (Amperes at 25°C)													
10.20	51.3	33.4	26.2	13.4	9.67	8.32	6.65	4.97	3.74	2.38	1.59	1.35	0.71
10.50	50.8	33.1	25.9	13.2	9.58	8.26	6.53	4.79	3.62	2.34	1.58	1.34	0.68
10.80	50.3	32.7	25.6	13.1	9.48	8.20	6.40	4.60	3.50	2.29	1.56	1.32	0.65
Constant Power Discharge Data Sheet (Watt at 25°C)													
10.20	563	406	328	185.5	135.2	102.9	78.89	59.35	42.36	27.92	19.66	15.91	8.57
10.50	539	392	319	181.6	132.1	101.2	77.74	58.51	41.40	27.6	19.50	15.68	8.45
10.80	511	378	308	176.4	128.8	99.55	76.58	57.67	40.68	27.28	19.30	15.41	8.33

# **Performance Characteristics**












#### FACTORY ADDRESS:

Road No.6, An Phuoc IP, An Phuoc Ward, Long Thanh District, Dong Nai Province, Vietnam







€ 0084-978366669
₩ 0084-2513686918

x <u>sales@saite.vn</u> ∰ <u>www.saite.vn</u>